

## **TECHNICAL DATASHEET**

## **LD 1925AS**

## PRODUCT DESCRIPTION

LD 1925AS is a Low Density Polyethylene with a Melt Flow Rate of 1.9 g/10min (190°C/2.16kg).

LD 1925AS is mainly recommended for shrink lm applications. It contains slip agent and antiblocking additives and has a suitable molecular structure to produce lm with excellent mechanical properties.

LD 1925AS can be easily processed on all types of extruders designed for polyethylene. The melt temperature is suggested to be in the range of  $160 - 190^{\circ}$ C. Excellent properties of the lm are achieved with a blow - up ratio of 2:1 and recommended lm thickness range from 25 to  $60 \, \mu m$ .

## TRPICAL APPLICATION

Bags & Pouches, Shrink Film, Food Packaging, Surface Protection.

TYPICAL DATA

Physical	Method	Unit	Values
Density	ISO 1183	g/cm <sup>3</sup>	0.925
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10min	1.90
Melting Temperature	ISO 3146	°C	111
Vicat Softening Temperature (A50 (50 °C/h 10N))	ISO 306	°C	94
Mechanical	Method	Unit	Values <sup>(1)</sup>
Tensile Modulus	ISO 527-1,-2	MPa	260
Tensile Stress @ Yield	ISO 527-1,-2	MPa	11
Tensile Strain @ Break (MD / TD)	ISO 527-1,-3	%	250 / 600
Tensile Strength (MD / TD)	ISO 527-1,-3	MPa	26 / 18
Dart Drop Impact (50 μm)	ASTM D 1709	g	110
Coefficient of Friction	ISO 8295	%	20
Optical	Method	Unit	Values <sup>(1)</sup>
Haze	ASTM D 1003	%	< 7
Gloss (20°) (60°)	ASTM D 2457	GU GU	> 50 > 100

<sup>(1) (</sup>The above properties are measured on blown film of  $70\mu m$  thickness, extruded at melt temperature of  $180^{\circ}C$  and a blow up ratio of 2:1)

Note: The typical properties are not to be construed as specifications.